



NSAI
Standards

Irish Standard
I.S. EN 14811:2019&LC:2019

Railway applications - Track - Special purpose rail - Grooved rails and associated construction profiles

I.S. EN 14811:2019&LC:2019

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

Published:

*This document was published
under the authority of the NSAI
and comes into effect on:*

2019-05-14

ICS number:

93.100

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

National Foreword

I.S. EN 14811:2019&LC:2019 is the adopted Irish version of the European Document EN 14811:2019, Railway applications - Track - Special purpose rail - Grooved rails and associated construction profiles

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

Compliance with this document does not of itself confer immunity from legal obligations.

In line with international standards practice the decimal point is shown as a comma (,) throughout this document.

This page is intentionally left blank

Correction Notice

Reference: EN 14811:2019

Title: Railway applications - Track - Special purpose rail - Grooved rails and associated construction profiles

Work Item: 00256603

Brussels, 2019-04-03

In accordance with CENELEC/BT Decision 139/C147, with reference to the above, please include the following minor editorial correction(s) in the document related to:

the following language version(s) :

- ☒ English
- ☐ French
- ☐ German

for the following procedure :

- ☐ PQ/UQ
- ☐ Enquiry
- ☐ 2nd Enquiry
- ☐ Parallel Enquiry
- ☐ 2nd Parallel Enquiry
- ☐ Formal Vote
- ☐ 2nd Formal Vote
- ☐ Parallel Formal Vote
- ☐ 2nd Parallel Formal Vote
- ☐ UAP
- ☐ TC Approval
- ☐ 2nd TC Approval
- ☒ Publication
- ☐ Parallel Publication

It has been brought to our attention that this document, issued on 2019-03-20, requires modification.

Please find enclosed the updated English version.

- In 8.2.1, Table 6, Footnote g: replace "60Ri3 or 63Ri1" with "60R3 or 63R1".
- In 8.3.3: replace "maximum of 0,5 m" with "maximum of 0,5 mm".
- In the explanation to Figure A.18: replace " $W_{xh}=91,9 \text{ cm}^3$ " with " $W_{yh}=91,9 \text{ cm}^3$ ".

We apologise for any inconvenience this may cause.

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 14811

March 2019

ICS 93.100

Supersedes EN 14811:2006+A1:2009

English Version

**Railway applications - Track - Special purpose rail -
Grooved rails and associated construction profiles**

Applications ferroviaires - Voie - Rails spéciaux - Rails
à gorge et profils de construction associés

Bahnanwendungen - Oberbau - Spezialschienen -
Rillenschienen und zugehörige Konstruktionsprofile

This European Standard was approved by CEN on 14 December 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	4
Introduction	6
1 Scope	8
2 Normative references	8
3 Terms and definitions	8
4 Information to be supplied by the purchaser	9
5 Steel grades	9
6 Dimensions, static properties, linear mass and tolerances	10
7 Manufacture	10
7.1 Product integrity	10
7.1.1 Factory production control	10
7.1.2 Best practice manufacture	10
7.2 Blooms	11
7.3 Grooved rails and associated construction rail profiles	11
7.4 Marking	11
7.4.1 Rolling marks	11
7.4.2 Hot stamping	12
7.4.3 Other identification	12
7.4.4 Exceptions	12
8 Acceptance tests	13
8.1 Laboratory tests	13
8.1.1 General	13
8.1.2 Chemical composition	13
8.1.3 Hydrogen	15
8.1.4 Hardness test	15
8.1.5 Tensile test	16
8.1.6 Retests	16
8.2 Dimensional and straightness tolerances	16
8.2.1 Profile	16
8.2.2 Straightness and twist	19
8.2.3 Cutting and drilling	19
8.2.4 Gauges	20
8.3 Surface imperfections	20
8.3.1 General	20
8.3.2 Protrusions	20
8.3.3 Depressions in the web and foot	21
8.3.4 Depressions in the running surface	21
8.4 Surface microstructural damage	21
8.5 Proving and dressing of surface imperfections	21
8.6 Determination of the linear mass	22
Annex A (normative) Grooved rail profiles and associated construction rail profiles	26
Annex B (normative) Gauges	79

Annex C (informative) Holes in grooved rails	98
Annex D (informative) Electric conductivity of the rails	100
Bibliography	101

EN 14811:2019 (E)**European foreword**

This document (EN 14811:2019) has been prepared by Technical Committee CEN/TC 256 “Railway applications”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2019, and conflicting national standards shall be withdrawn at the latest by September 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14811:2006+A1:2009.

This revision introduces new profiles, and technical changes on drawings and technical data.

Other standards on rails include:

EN 13674, *Railway applications — Track — Rail*, that comprises the following parts:

- *Part 1: Vignole railway rails 46 kg/m and above;*
- *Part 2: Switch and crossing rails used in conjunction with Vignole railway rails 46 kg/m and above;*
- *Part 3: Check rails;*
- *Part 4: Vignole railway rails from 27 kg/m to, but excluding 46 kg/m.*

Other standards for rails and corresponding welding processes, already published or under preparation, are:

- EN 14587-1, *Railway applications — Infrastructure — Flash butt welding of new rails — Part 1: R220, R260, R260Mn, R320Cr, R350HT, R350LHT, R370CrHT and R400HT grade rails in a fixed plant;*
- EN 14587-2, *Railway applications — Track — Flash butt welding of rails — Part 2: New R220, R260, R260Mn and R350HT grade rails by mobile welding machines at sites other than a fixed plant;*
- EN 14587-3, *Railway applications — Track — Flash butt welding of rails — Part 3: Welding in association with crossing construction;*
- EN 14730-1, *Railway applications — Track — Aluminothermic welding of rails — Part 1: Approval of welding processes;*
- EN 14730-2, *Railway applications — Track — Aluminothermic welding of rails — Part 2: Qualification of aluminothermic welders, approval of contractors and acceptance of welds;*
- EN 15594, *Railway applications — Track — Restoration of rails by electric arc welding;*
- EN 16273, *Railway applications — Track — Forged rail transitions;*
- EN 16725, *Railway applications — Track — Restoration and repair of manganese crossings;*
- EN 16771, *Railway applications — Infrastructure — Aluminothermic welding of grooved rails.*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 14811:2019 (E)

Introduction

This Introduction provides an explanation of the concept and reasoning for preparing this document. Its description ensures that, during any future revisions, restrictions will be removed if technical progress has been made or will be kept if this is not the case in order that safety is maintained if new manufacturers, products and technologies appear.

The most commonly used delivery conditions in Europe for the supply of grooved rails and associated construction rail profiles have been reviewed during the preparation of this document. Modern rail production technology and the requirements of commuter railways within the European Union have demanded that the technical requirements for the products specified in this standard be reconsidered.

Whenever possible, this document is performance-based. It recognizes the European quality management standard EN ISO 9001 and requires manufacturers to offer the latest proven technology consistently to satisfy the demanding quality of the required product.

The steels are classified according to hardness and not to tensile strength.

The acceptance tests were developed in order to monitor the properties of the grooved rail steels and grooved rails and associated construction rail profiles that are of importance for the production of grooved rails and associated construction rail profiles and which comply with the demands of commuter railways.

The steel grades covered by this document reflect trends in commuter railway usage and heat-treated rails as well as associated construction rail profiles. This document contains profiles for grooved rails and associated construction rail profiles for grooved rail facilities having a linear mass of 42 kg/m and above.

To ensure the supply of high quality rails, some restrictions on production processes have been imposed.

This standard is applicable to all procurements covered by the European Procurement Directive (Directive 2014/24/EU of the European Parliament and of the Council of 26 February 2014). Additionally, CEN has requested a performance-based standard taking into account safety requirements and the application of the most recent technologies. With respect to the Directive, it is acknowledged that there are (and with respect to safety requirements also shall be) options to deviate from the standard upon agreement between purchaser and manufacturer.

This document reflects the change in philosophy compared with the traditional content of delivery conditions for grooved rails and associated construction rail profiles. The most frequently used delivery conditions in Europe for the supply of grooved rails and construction rail profiles have been reviewed. All the aspects that are important for the purchasers and manufacturers have been analysed to ensure that the overall contents are particularly appropriate and relevant for the document. For example, the classification of the steel grades of grooved rails and associated construction rail profiles and also other aspects of the document has been based on hardness, not on tensile testing. Whilst the two are directly related, hardness testing is very quick and inexpensive to carry out and provides more relevant guidance to the user, particularly where properties vary in different parts of the profile.

One new aspect of the document is the integration of a clause on quality management and testing in order to ensure the product integrity.

In order to ensure that the quality management systems are consistent for all manufacturers and that all purchasers can be sure about the consistency of the product quality of these safety-related components, this document recommends that the manufacturer operates a quality management system at least equivalent to the requirements of a quality management standard such as EN ISO 9001. This makes it possible to dispense with detailed requirements on tests and comprehensive testing.

Ideally, manufacturing methods should not be referred to in product standards. However, some rail properties are either not exactly known or cannot be determined with an adequately high statistical reliability. In these cases, as the final possibility, reference is made to manufacturing methods that correspond to best practice. Methods and requirements are specified that offer the maximum probability that the necessary product is obtained in the track. Future technological solutions can increase the list of these requirements but will preferably reduce them.

Examples of where today's technology is taken as the basis, but developments are progressing, are:

- determination of hydrogen content;
- minimum area reduction for rolling of grooved rails and associated construction rail profiles;
- roller straightening effects on contact scrub.

EN 14811:2019 (E)

1 Scope

This document specifies requirements for grooved rails and associated construction rail profiles for grooved rail facilities with a linear mass of 42 kg/m and upwards for use in tram transport systems.

NOTE Grooved rails are also used for harbour and industrial tracks.

Five pearlitic steel grades are specified in a hardness range between 200 HBW and 390 HBW. The rails are either non-heat-treated or heat-treated and are made from non-alloyed (C-Mn) steel in both cases.

This document specifies 26 specific grooved rail profiles and 7 specific construction rail profiles. The grooved rail profiles can also be used as construction elements in switches and crossings.

Two grooved rail classes are specified differing in requirements for profile tolerances.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1)*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

heat

liquid steel melt tapped out of a converter or electric arc furnace which after continuous casting includes a given number of blooms relating to the weight of the heat and the extent of the mixing zone

Note 1 to entry: In the case of sequence casting, the blooms belonging to the mixing zone will be clearly defined.

3.2

sequence

number of heats of the same steel grade which undergo continuous casting in a new or repaired tundish

Note 1 to entry: Tundishes can be used in parallel if the caster has many strands.

3.3

heat-treated rail

rail that has undergone accelerated cooling from austenitizing temperature during the metallurgical transformation period

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-